

METAL CLEANERS

PRESOL	METAL BASE		g/l	TEMP °C	A/dm2		
1307	FE	INMERSION	50 A 80	40 A 70	-		
7067	FE	electrolitico	70 A 100	35 a 70	3 a 8	anodico	
1012	FE	electrolitico	70 a 110	70 a 80	2.5 a 10	anodico	
1478	LA, CU, FE	INMERSION	45 A 75	60 A 82		-	
1478	ZAMAC,LA, CU	electrolitico	45 A 75	60 A 82		ANODICO	
1012	FE	electrolitico	70 A 110	40 A 80	2.5 a 10	ANODICO	
5323	FE	electrolitico	45 a 90	70 a 90	2.7 a 12	anodico	no phosph
5123	FE, LA	INMERSION	45 a 80	45 a 70	-	-	no phosph
3090	LA	INMERSION	50 a 80	75 a 90			hidrofobico
3090	LA	Ultrasonido	30 a 50	75 a 90			
1083	LA, cu	electrolitico	60 a 80	25 a 40	2 a 4	Catodic/anodic	
1304	Fe						

